

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 469 735 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
10.06.1998 Bulletin 1998/24

(51) Int Cl.⁶: **G03F 7/36**

(21) Application number: **91306276.6**

(22) Date of filing: **11.07.1991**

(54) Device for forming flexographic printing plate

Vorrichtung für die Herstellung von flexographischen Druckplatten

Appareil pour la formation d'une plaque pour l'impression flexographique

(84) Designated Contracting States:
DE FR GB IT

(30) Priority: **31.07.1990 US 560619**

(43) Date of publication of application:
05.02.1992 Bulletin 1992/06

(73) Proprietor: **MINNESOTA MINING AND
MANUFACTURING COMPANY**
St. Paul, Minnesota 55133-3427 (US)

(72) Inventors:

- **Peterson, John A., c/o Minnesota Mining and
St. Paul, Minnesota 55133-3427 (US)**
- **Fell, Kurt F. F., c/o Minnesota Mining and
St. Paul, Minnesota 55133-3427 (US)**

- **Lien, Craig D., c/o Minnesota Mining and
St. Paul, Minnesota 55133-3427 (US)**
- **Staus, Gary A., c/o Minnesota Mining and
St. Paul, Minnesota 55133-3427 (US)**
- **Martens, John A., c/o Minnesota Mining and
St. Paul, Minnesota 55133-3427 (US)**
- **VanDerWerff, Gary D., c/o Minnesota Mining and
St. Paul, Minnesota 55133-3427 (US)**

(74) Representative: **Baillie, Iain Cameron et al**
c/o Ladas & Parry
52-54 High Holborn
London WC1V 6RR (GB)

(56) References cited:
DE-A- 1 422 942 **US-A- 3 264 103**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 469 735 B1

Description

The present invention relates to flexographic printing. In particular, it relates to devices for forming flexographic printing plates.

"Flexography" applies to a printing format which uses a flexible substrate bearing an elastomeric or rubbery relief printing surface. A "composite" film is one with multiple layers, the adjacent layers being formed from different materials. "Elastomer" and "elastomeric" refer to rubbers or polymers having resiliency properties similar to those of rubber. In particular, elastomers are capable of being substantially elongated and then returned to their original dimensions upon release of the stress elongating the elastomer. In all cases an elastomer must be able to undergo at least 10% elongation (at a thickness of 0.5 mm) and return to its original dimensions after being held at that elongation for 2 seconds and after being allowed 1 minute relaxation time.

More typically an elastomer can undergo 25% elongation without exceeding its elastic limit. In some cases an elastomer can undergo elongation to as much as 300% or more of its original dimensions without tearing or exceeding the elastic limit of the composition. Elastomers are typically defined to reflect this elasticity as in ASTM Designation D883-866 as a macro-molecular material that at room temperature returns rapidly to approximately its initial dimensions and shape after substantial deformation by a weak stress and release of the stress. Generally, such compositions include relatively high molecular weight compounds which, upon curing, form an integrated network or structure. The curing may be by a variety of means, including the use of chemical curing agents, catalysts, and/or irradiation.

The first flexographic printing plates were produced from natural or synthetic rubber compositions which were chemically cured under heat and pressure in a mold using conventional rubber curatives such as mercapto compounds. Recently, photopolymer elastomeric compositions (elastomer containing compositions curable upon exposure to actinic radiation) useful to produce relief printing plates have been described. For example, U.S. Patents 4,369,246 and 4,423,135 describe solvent-insoluble, elastomeric printing relief plates which are formed by applying to a flexible polymer film substrate layer a layer of a photosensitive composition. A cover sheet is laminated to a surface of the photosensitive layer to form a flexible film. A flexographic plate is then formed by stripping off the cover sheet, imagewise exposing the composition layer to actinic radiation through the film, and removing the film and unexposed areas of the composition layer by solvent washing. Another known plate forming process is similar to the process described above, except that the relief areas of the plate are produced by washing out the areas not exposed to radiation with an aqueous developer.

With both the aqueous and solvent washing methods described above, multiple processing steps are required which are time consuming and are therefore expensive. In addition, these technologies produce potentially toxic by-product wastes when forming flexographic plates.

Due to the limitations of the above-mentioned prior art methods of forming flexographic printing plates, a new family of radiation curable polyurethane elastomers was developed which has the advantage of being useful to form flexographic printing plates without requiring the use of solvents or aqueous wash systems. U.S. Patent Application Serial No. 557,969 entitled "Printing Plate Compositions", was filed on July 26, 1990 by Martens, one of the co-inventors of this invention, (hereinafter the "Martens composition application"). This application discloses flexographic printing plate compositions.

A flexographic printing plate 11 formed by a compound disclosed in the Martens composition application is shown in cross-section in Figure 1. The printing plate 11 has a first base layer 15 which may be a polymer or a metal. Preferred polymers include polyester, polycarbonate, or polyimide, for example. The base material can also be made of steel or aluminum, for example. The base material is selected to be tear resistant and must have a fairly high melt point, for example, above the melt temperature of the next layer formed on the base layer. A second substantially uniform layer 17 is applied onto the base layer. The second layer is formed of a radiation curable polymer such as a polyurethane elastomer. The elastomer layer may be adhesively or chemically bonded to the base material (not shown). The base layer in combination with the radiation curable polymer together forms a "flexible film."

The flexible film is next exposed to actinic radiation from a surface 23 of the base layer 15 to chemically cross-link and cure a portion of the second layer 17 to form a floor layer 25 as described in Martens application having the title "Flexographic Printing Plate Process," by John Martens, a co-inventor of the present invention, Serial 558,301, filed July 26, 1990, (hereinafter the "Martens process application"). A portion of the film is imagewise exposed to actinic radiation from the opposite surface 27 and a visible image appears in the exposed areas of the radiation curable layer.

The portions 29 of the flexible film exposed to radiation chemically cross-link and cure. The cured portions have an elevated melting temperature, and are insoluble in flexographic printing inks under normal conditions. "Normal" conditions include printing plate temperatures of between 11.6°C (53 degrees Fahrenheit) and 31.1°C (88 degrees Fahrenheit).

An absorbent material is selected having a melt temperature exceeding the melt temperature of the unexposed or "uncured" portions of the radiation curable composition and having good tear resistance at the same operating temperatures. Preferably, the selected material withstands temperatures required to process the film at an unsteady

state, for example, where the plate does not reach a state of thermal equilibrium during heating. The absorbent sheet contacts a surface 27 of the radiation curable layer of the heated flexible film, and absorbs the liquified portions 31 of the elastomer off of the upper surface, forming a flexographic printing plate 11. As described in the Martens process application, it is necessary to bring the most preferred printing plate and a sheet of the most preferred absorbent material into contact three times to remove the liquified, uncured elastomer.

The printing plates as described in the Martens process application are heated to between 31.1°C and 155.5°C (88 and 312 degrees Fahrenheit) and while in contact with the absorbent layer, the uncured composition liquifies and flows into the absorbent layer. It is preferred that most of the composition in the uncured areas be removed from the flexible substrate and be absorbed into the absorbent material.

It is also desirable that the elevated temperatures used to cause the uncured composition to flow (reduce its viscosity, or exceed its softening temperature, e.g., see ASTM designation D 1238-86) into and be absorbed by the absorbent layer should not distort the flexible substrate or the hardened composition by more than 2% in any surface dimension. The actual temperatures will vary with the specific substrate and composition used.

Following curing of portions of the elastomeric layer, the uncured portions are removed to reveal a raised structure which becomes the printing surface of the plate. The "relief" portions are the raised portions of the flexographic printing plate which are coated with ink and which contact print media. The relief structure is bound to the support layer by physical and/or chemical action and remains in place during the printing process through repeat impressions. The exposed surface of the cured elastomeric layer therefore becomes the ink receiving surface which both receives ink from the inking row and transfers it to the substrate to be printed during the printing process.

The hardening or curing step of the process (by irradiation) can also act to increase the adhesion of the composition to the substrate. This can be by direct adhesion of the curing composition to the substrate, for example, either chemical adhesion by reaction or physical adherence to surface structure on the flexible layer. The primer layer may be photo-sensitive or photoinsensitive to aid in this adherence effect. Flexographic plates having a layer for forming relief images are preferably formed from polymers which have a low melt temperature, a high melt index, are radiation curable, and are elastomeric polyurethane compositions. The composition should have sufficient resistance to swelling after curing. The cured elastomer compositions should be particularly resistant to increases in volume and swelling when immersed in flexographic inks, such as water based inks utilized in the flexographic printing process. This low swell feature is critical to the ultimate printing quality achieved with the printing plate because swelling causes the dimensions of the relief image to enlarge.

The press life or wear life of the plate on press (the number of impressions until failure occurs) may also be greatly reduced by swelling which may result in a loss of physical strength of the cured elastomer composition. Radiation curable polyurethane printing plates cure or cross-link when exposed to actinic radiation without the need of additional vinyl containing monomeric additives, such as monomers containing more than one vinyl group per molecule. Using a curing process which does not require the use of solvent avoids the harmful effects on the environment caused by pollution.

Radiation curable elastomer coated sheet material is resistant to cold flow during storage. Elastomers which undergo too much cold flow result in printing plates having unacceptable variation in plate thickness. The radiation curable polyurethane elastomers have good to superior resistance to cold flow prior to irradiation induced cross-linking or curing.

The use of flexographic printing plates is popular because the process is a "direct" printing process. The printing plate and its temporarily bound ink layer are in direct contact with the substrate, for example, the paper or film being printed. Before the Martens inventions, no devices existed to process flexographic printing plates by liquifying a portion of the flexible sheet, and removing the liquified portions with an absorbent material.

US-A-3,264,103 discloses a process for preparing a relief printing plate which comprises: (1) exposing to actinic radiation through an image-bearing transparency, a solid photopolymerizable thermoplastic stratum, attached to a support; (2) heating said stratum to a temperature between the flow temperatures of the exposed and the underexposed stratum materials; and (3) pressing a porous matrix into contact with said heated stratum to transfer at least about 80% of the molten unexposed material by absorption and leaving a relief image on said support.

SUMMARY OF THE INVENTION

The present invention is a mechanical device for forming a flexographic printing plate, the plate preferably being formed from a sheet of imagewise irradiated film formed according to the flexographic printing plate process disclosed in the Martens process application. The device forms a flexographic printing plate from a sheet of film having at least one layer capable of being partially liquified. The device includes heating means for applying heat to the sheet of film for an amount of time and at a temperature sufficient to cause a portion of the layer to liquify. The most preferred heating means includes an electrical heating blanket. The blanket is mounted onto an inner surface of a rotatable preheating drum which supports the sheet of film and preheats the film to a temperature near the melting point of the uncured portions of the layer. The heating means of the preferred embodiment also includes an electrical core heater

mounted in a substantially cylindrical cavity of a hot roller. The core heater heats the hot roller to an outer skin temperature which exceeds the melting point of the uncured portions of the film.

The preferred embodiment also includes a first delivery means for supplying an absorbent material to a surface of the layer. In the preferred embodiment, the first delivery means includes a motor which rotates a drive shaft, which in turn rotates a drive roller capable of pulling a continuous web of absorbent material from a supply roll, over a hot roller. The absorbent material contacts the hot surface of the hot roller. The present invention also includes a second delivery means for delivering a sheet of film to the heating means comprising a rotating preheating drum having a transversely positioned clamp, the clamp securing the leading edge of the sheet of film onto the outer surface of the preheating drum as the drum rotates. The drum is heated with an electrical blanket in the preferred embodiment to bring the film up to near the melt temperature of the uncured portions of the polymer layer.

The present invention also includes pressure means for causing a surface of the film and the absorbent material to come into face-to-face contact. The pressure means in the preferred embodiment includes a series of springs for biasing the hot roller against the preheating drum. A pneumatic cylinder is provided which drives the heating roller and absorbent web toward and into contact with a surface of the sheet of film which in turn contacts the film on the preheating drum. The pressure means in the preferred embodiment applies pressure sufficient to cause at least a portion of the liquified material to be absorbed by the absorbent material. The present invention also includes separation means for separating the film from the absorbent material, immediately after the desired amount of liquified material is removed from the plate.

Thus this invention provides a device (10) for forming a flexographic printing plate (11) the plate being formed from a sheet of film having at least one layer (17) capable of being partially liquified, comprising:

heating means for applying heat to said sheet of film for an amount of time and at a temperature sufficient to cause a portion of said layer to liquify the heating means comprising a hot roller (78) mounted for rotation into a first portion of a frame wherein the hot roller has an outer surface coated with an elastomer;

first delivery means for supplying an absorbent material to a surface of said layer of said sheet of film;

second delivery means for delivering the sheet of film to said heating means, wherein the second delivery means comprises a preheating drum (18) mounted for rotation in a second portion of the frame wherein at least one of the first and second frame portions are moveable relative to the other, wherein the preheating drum is formed from a substantially cylindrical wall portion (172), having a cavity defined by an inner surface of the cylindrical wall portion,

a hub (174, 176) at each end, and means for attaching the hubs to the cylindrical wall portion to allow for thermal expansion,

pressure means for causing a surface of said layer and the absorbent material to come into face to face contact between the preheating drum (18) and the hot roller (78) at a pressure sufficient for at least a portion of the liquified

material to be absorbed by the absorbent material; and

separation means for separating the film from the absorbent material.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a schematic cross-sectional view of a formed printing plate, showing a multilayered construction.

Figure 2 is a perspective view of a first preferred embodiment of the device of the present invention.

Figure 3 is a detailed side elevational view of the actuators of the first preferred embodiment.

Figure 4 is a detailed side cross-sectional view of the second delivery means.

Figure 5 is a detailed drawing of the pneumatic cylinder ends.

Figure 6 is a side cross-sectional view partially in schematic of a first embodiment of the present invention.

Figures 7A-7D are a series of heat up curves used to form the present invention.

Figure 8 is a side cross-sectional view partially in schematic of the present invention with the hot roller engaged.

Figure 8A is a detailed side elevational view of the pressure limiting device of a preferred embodiment of the present invention.

Figure 9 is an end elevational view, partially cut out of the first embodiment of the present invention.

Figure 10 is a side elevational view of the preheating drum.

Figure 11 is a more detailed view of the gear and pinion.

Figure 12 is a side cross-sectional view of the drum taken along line 12--12 as shown in Figure 2.

Figure 13 is a side elevational view of the hub of the preheating drum.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention is a device for heat developing flexographic printing plates. A first preferred embodiment of

a device of the present invention is a plate processor 10 shown in Figure 2. The plate processor 10 of the present invention accepts a previously formed and previously imagewise actinic radiation exposed flexible sheet 16, the sheet having a base layer and an adjacent layer of a radiation hardenable elastomer material (curable layer). The base layer has a preferred thickness of from about 0.1270 mm to about 0.1778 mm, with a preferred thickness of about 0.1778 mm. The radiation curable layer is between about 0.3556 mm and about 0.8890 mm thick, with a preferred thickness of about 0.5080 mm thick. A portion of the radiation curable layer is cured by actinic radiation through the lower surface 23 of the base as shown in Figure 1 to form a cured "floor 25." Next, the film is imagewise exposed from the opposite surface 27 to cure the desired portions of the plate. The floor 25 is from 0.1778 mm to about 0.2540 mm thick with a preferred thickness of about 0.1778 mm.

The remaining portion of the radiation curable layer 17 after curing consists of cured portions 29 and uncured portions (not shown). The layer containing cured as well as uncured portions has a thickness between about 0.1778 mm and about 0.6350 mm, with a preferred thickness of about 0.3800 mm.

Examples of flexible film compositions suitable for forming the curable layer are disclosed in the Martens composition application. Although the most preferred embodiment of the invention heat develops a radiation curable polyurethane elastomer disclosed in the Martens composition application, the device of the present invention is adaptable to heat develop other flexographic printing plate films such as PLS Printing Plates manufactured by E. I. Du Pont de Nemours & Co. of Wilmington, Delaware. Before the present invention, the PLS printing plates were developed using solvents. Although PLS printing plates can be processed on the device of the present invention, the Din Pont product is less suitable than the Martens printing plates because the Martens plates do not emit fumes during heat processing as do the PLS print plates. The device of the present invention is also not limited to heat developing flexographic printing plates. The present invention contemplates a device capable of heating a layer of flexible film capable of being partially liquified to a temperature sufficient to melt at least a portion of a layer of the flexible film for any purpose.

For purposes of illustration only, a device capable of heat developing flexographic printing plate film disclosed in the Martens composition application will be described. In particular, the first preferred embodiment is adapted to process film such as 3M Brand Flexoplate™ available from Minnesota Mining and Manufacturing Company of St. Paul, Minnesota.

The first preferred embodiment of the present invention as shown in Figure 2 includes a support frame 12 (shown schematically in Figure 6) and a feed tray 14 mounted onto the support frame 12, the feed tray 14 being of a size and a shape suitable for accepting a flexible sheet of film 16.

Although the size of the sheets suitable for being developed by the plate processor 10 is unimportant to the present invention, the first preferred embodiment is capable of processing sheets 14 up to 35.56 centimeters in width and up to 71.12 centimeters in length. The most preferred film dimensions are 22.54 centimeters in width by 43.18 centimeters in length. The most preferred total composite film thickness is between 0.4826 mm and 1.0668 mm, with a preferred thickness of about 0.5715 mm (the thickness of the above-mentioned 3M product).

Prior to using a device of the present invention to heat develop a sheet of film 16 to form a flexographic printing plate, a template or mask is placed over the film and the film is imagewise exposed to actinic radiation to harden a portion of the radiation curable layer. The Martens process application discloses the most preferred method of forming, irradiating, and heat developing a flexographic sheet. The Martens process application is herein incorporated by reference.

The Martens process is briefly described below. A composite film as described in the Martens composition application is formed. The film is imagewise irradiated, and then is heated to between 31.1°C and 155.5°C (88 degrees Fahrenheit and 312 degrees Fahrenheit), depending upon the exact composition selected. As the film temperature approaches the melting temperature of the uncured portions of the radiation hardenable composition layer, the film comes into contact with a preheated absorbent web of nonwoven material. The most preferred nonwoven material is available from the James River Corporation of Richmond, Virginia under the trade name "Cerex.™" The heat in the absorbent web is transferred to the flexible film upon contact, and the temperature of the flexible film is raised to a temperature sufficient to enable the uncured portions of the composition layer to liquify and be absorbed into the absorbent layer.

Pressure is applied to force the absorbent web into intimate contact with the film. The most preferred contact force is not known. However, it is believed that between 68.9 kPa and 689 kPa (10 p.s.i and 100 p.s.i) is adequate to enhance the absorption from the film surface to the absorbent web without distorting the composite film.

At least 75% of the liquified composition in contact with the absorbent web is absorbed. In the preferred embodiment, most of the uncured portions are removed. The web is then removed from the film immediately after absorption, before the molten polymer is able to resolidify. The molten material then resolidifies in the absorbent web.

The plate processor 10 of the present invention includes a preheating drum 18 which in the illustrated embodiment rotates counter-clockwise from the first side 19 of the machine. The preheating drum 18 is elevated to a temperature sufficient to raise the temperature of the uncured portions of the radiation curable layer near its melt point. In the preferred embodiment, the preheating drum is operated at a temperature between 93.3°C and 137.7°C (200 and 280

degrees Fahrenheit), with a preferred operating temperature of about 135°C (275 degrees Fahrenheit).

At the same time, the substrate layer is of a much higher melt temperature, for example, exceeding the operating temperature of the preheating drum 18, and therefore the mechanical properties of the substrate are not significantly altered by this preheating step.

The preheating drum 18 has a flush mounted clamp 20 mounted transversely on the outer surface 22 of the drum for securing a leading edge 24 of the flexible sheet of film 16 to the outer surface 22 of the drum. The clamp 20 in the preferred embodiment is elongated and has a plurality of teeth 26 extending tangentially in a direction opposite the direction of rotation of the drum. In operation, the clamp 20 is raised radially outward and off of the outer surface 22 of the preheating drum 18 by an actuator means 28 shown in Figure 3. In the preferred embodiment, the actuator means 28 is a pair of pneumatic cylinders 30, mounted onto the frame 12, and positioned on opposite ends of the preheating drum 18. The pneumatic cylinders are mounted radially at approximately a 30 degree angle from the vertical. The pneumatic cylinders 30 each have an end 32 (shown in Figure 5) with a stop 34 which exerts a radial force away from the axis of rotation 36 (into the paper) of the preheating drum 18. The operation of the actuation means 28 will be more clearly understood by first examining the features of the clamp 20 as shown in Figure 4.

The clamp 20 is substantially elongated. In the preferred embodiment, the clamp 20 extends the full width of the film 16. In the preferred embodiment, the clamp is about 36.83 centimeters wide. A plurality of support legs 38 are fixedly mounted onto a lower surface of the clamp 20, and extend through the drum wall and into the interior portion of the preheating drum 18. The support legs 38 in the preferred embodiment are cylindrical, and are fixedly connected to a transverse rod 40 which in the preferred embodiment is formed from rectangular bar stock.

At each end of the transverse rod 40 is a cam follower 42 rotationally mounted along an axis 44 passing substantially through the center of the rod 40. The cam followers 42 in the preferred embodiment are substantially cylindrical. The length of the rod 40 without the cam followers 42 in the preferred embodiment is slightly shorter than the width of the drum 18, and the cam followers 42 extend outwardly of the sides of the drum 18.

A first end 32 as shown in Figure 5 of pneumatic cylinder 30 retracts in a direction shown by arrow 48 in response to a signal from the controller (not shown). The controller (not shown) is programmable and operable from a control panel 50 (shown in Figure 2). The control panel in the preferred embodiment includes many features such as an on/off switch, a selector switch for selecting the number of cycles per sheet required, an open and close switch to operate clamp 20, a plurality of indicator lights for determining the cycle the machine is in and L.E.D. readouts to indicate operating temperatures, for example.

Each first end 32 has a stop 34 which extends in a direction substantially parallel to a central cylinder axis 44 of the cam follower 42. The stop 34 engages the cam follower 42, and allows the pneumatic cylinder 30 (shown in Figure 3) to lift the transverse rod 40 and clamp 20 upwardly (shown in Figure 4), away from the central rotational axis 36 (as shown in Figure 3) of the drum 18. The clamp 20 is opened by a manual switch when the preheating drum 18 is at rest. The first preferred embodiment also has a second pair of actuators 54 as shown in Figure 3 which are also pneumatic cylinders 56, and are rigidly mounted onto the frame 12. The pneumatic cylinders 56 each have a first end 58 having a stop 60 (shown in Figure 5) for receiving the same cam followers 42 at a different rotational location and when the preheating drum 18 is in motion. The size and shape of the stops 60 are curved and larger than stops 34 because stops 60 engage the cam followers 42 during rotation, while stops 34 engage the same cam followers 42 when stationary.

Referring back to Figure 4, between the clamp 20 and the transverse rod 40 and fixedly attached to the clamp 20 and the rod 40 are support legs 38. Tensioning springs 62 extend around each support leg 38 and hold the clamp 20 substantially flush with the outer surface 22 of the drum when no other forces are being applied to the cam followers 42.

The clamp 20 must lift to a height sufficient to provide enough clearance for inserting the leading edge 24 of the flexible sheet of film 16 into an opening defined by a lower surface 64 of the clamp 20 and a clamp receiving surface 66 of the preheating drum 18. The sheet 16 need only be positioned about 1.27 centimeters under the teeth 26 of clamp 20 to hold the sheet into place.

The lower surface 64 of the clamp 20 has a downwardly projecting edge 68 which tightly grips the film 16 and holds the film 16 in place on the drum 18.

Upon activating the control panel 50 (shown in Figure 2), the preheating roller 18 should be in the "start" position. If not, the controller actuates the preheating drum drive motor 73 (shown in Figure 6) and advances the preheating drum 18 to the "start" position, where the clamp 20 is slightly above a front edge of a feed plate 70. A cam activated microswitch 71 (shown in Figure 6) sends a signal to the controller to stop the drum when the drum 18 reaches the "start" position.

Feed plate 70 is inclined slightly to urge the leading edge 24 of the sheet 16 toward the clamp 20. A manual switch (not shown) is energized in the preferred embodiment to activate the pneumatic cylinders 30 (shown in Figure 3) which lift clamp 20 upwardly and holds the clamp 20 in an "open" position. A second manual switch (not shown) is activated, closing the clamp. A third "start" switch (not shown) activates a control sequence. After the "start" switch is activated, the drive motor 73 (shown in Figure 6) begins to rotate the drum 18. The drum 18 rotates at a preferred speed of about

40.64 linear centimeters per minute, as measured on the drum surface.

The preheating drum 18 in the first preferred embodiment is equipped with a preheating means which is an electrical heating blanket 21, available from the Watlow Electric Company of St. Louis, Missouri. The most preferred heating blanket is a wire wound blanket, having a 0.1143 cm. thickness, a 45.72 cm. width, and a 60.96 cm. length. The heating blanket has a 2000 watt capacity and requires a 220 volt energy supply. Any means of heating the drum is acceptable, as long as the power capacity of the heating means is sufficient to maintain a fairly constant selected skin temperature on the outer surface of the preheating drum 18 of about 135°C (275 degrees Fahrenheit).

The preheating drum 18 in the preferred embodiment is coated with a silicone rubber composition layer 75 having a Shore A hardness rating of about 55. The most preferred rubber coating is 0.48 cm. thick silicone rubber and is impregnated with aluminum particles. This type of rubber coating is available from Robinson Rubber Products Company, Inc. of New Hope, Minnesota. It is believed that the aluminum particles improve the heat transfer characteristics of the drum by between 10 to 20 percent.

The hardness of the coating layer 72 is important, although not critical to the invention. Flexible coatings having a Shore A hardness between 30 and 60 are suitable for covering the preheating drum 18 of the present invention.

The most preferred embodiment of the present invention is shown schematically in Figure 6. The preheating drum 18 is mounted for rotation on a stationary support frame 12 and rotates in a counterclockwise direction as indicated by arrow 72. A sheet of film 16 (shown in Figure 2) is placed on a surface 13 of a feed tray 14 and is urged in a direction indicated by arrow 74. The leading edge of a flexible sheet of film 16 is inserted into clamp 20. The sheet 16 remains on the surface 22 of the preheating drum during processing.

The plate processor 10 of the present invention includes a delivery means for feeding a continuous web 76 of nonwoven material which in the preferred embodiment contacts a hot roller 78. The hot roller 78 elevates the temperature of the web 76 to a temperature exceeding the melt temperature of the upper layer of the film. The heated web transfers heat to the flexible sheet of film, melts a portion of the layer and absorbs at least a portion of the liquified polymer.

In the first preferred embodiment of the present invention, a take-up roll 80 is provided for winding the nonwoven material after processing. In the preferred embodiment, the take-up roll 80 is independently belt driven by a variable speed motor 82.

Although the specific type of absorbent material is not critical to the present invention, the most preferred nonwoven material is Cerex™. The selection of the web material 76 depends in large part upon the thickness of the flexible sheet of film 16 to be processed, the melting temperature of the absorbent material, the heat transfer characteristics of both the flexible sheet of film 16, and the nonwoven material, and the strength of the absorbent material during the separation of the material from the film 16.

In order to determine the processing temperatures, speeds and other design criteria, it is first necessary to select the type of flexible sheet of film 16 to be processed and then to study its heat transfer characteristics.

A substantially rectangular hot plate was provided to collect the heat transfer data on the most preferred film. The temperature of the hot plate was raised to a temperature above the melt temperature of the irradiation curable layer, and maintained at that temperature for the first experiment. The most preferred absorbent material (Cerex™) was placed on the hot plate. Then a sheet of the flexible film, substrate side up was placed on the absorbent material. The surface temperature of the hot plate, as well as the temperature of the back of the base layer were measured over time.

A plot of polymer temperature at the film surface, at a 0.254 millimeter depth in the polymer was generated. A 0.5842 millimeter thick test film was used in the experiments. Temperature was plotted on the Y axis and time was plotted on the X axis. The curves were hyperbolic in shape and asymptotic to the controlled surface temperature of the hot plate. Figures 7A-7D are heat up curves for the most preferred film composition (3M Flexoplate™ manufactured by Minnesota Mining and Manufacturing Company of St. Paul, Minnesota) at various temperatures. The temperature of the hot plate was selected as a temperature exceeding the known melt temperature of the uncured portions of the flexible film.

Based on the shape of the curve of Film Surface Temperature v. Time, data was fitted into an equation of the type:

$$\text{Temperature} = \text{Time}/(a + b \times \text{Time})$$

The above-mentioned equation forms a straight line when time/temperature is plotted against time. The equation was solved for constants a and b at two different temperatures as well as at two different composite film thicknesses. Constants a and b were computed for various temperatures and thicknesses as summarized in Table I.

Table 1

Constants		Temperature		Thickness	
a	b	°F		(Mils)	
			°C		μm
0.019	0.00392	250	121	29	736.6
0.012	0.00383	250	121	16	406.4
0.017	0.00287	365	185	29	736.6
0.0067	0.0027	365	185	16	406.4

The correlation coefficients for the above equations were each greater than 0.90.

Next an equation was generated to relate constants a, b, the temperature and the thickness of the plate. The following model assumes that all material at the beginning of testing are at room temperature, and that the heat conductivities of each of the materials are equal.

$$a = 8.46 \times 10^{-3} - 3.17 \times 10^{-5} \times \text{temp} + 6.65 \times 10^{-4} \times \text{thickness}$$

$$b = 6.02 \times 10^{-3} - 9.43 \times 10^{-6} \times \text{temp} + 9.61 \times 10^{-6} \times \text{thickness}$$

The temperature units were in degrees Centigrade and Fahrenheit and the thickness units were in μm and mils (0.0254 mil/mm).

These relationships were used to generate curves relating temperature and a given depth in the polymer versus various surface temperatures and times.

The model was used to create curves for four different surface temperatures (204, 177, 163 and 149°C) (400, 350, 325 and 300 degrees Fahrenheit). The model also assumed that sufficient energy was provided to the plate to maintain a constant plate temperature. Based on the heat-up curves of Figures 7A-7D, a heating temperature of about 182°C (360 degrees Fahrenheit) was selected as a starting point in determining the maximum running speed and the heating temperatures of the hot roller 78.

In the most preferred embodiment, the preheating drum 18 as shown in Figure 6 has an outer diameter of approximately 25.88 centimeters and a width across the drum of about 48.26 centimeters. In order to adequately preheat the flexible sheet of film 16, it is necessary to heat preheating drum 16 to a selected temperature of approximately 135°C (275 degrees Fahrenheit), plus or minus about 5 degrees for a selected drum speed of about 40.64 linear centimeters per minute.

The preheating drum 18 in the preferred embodiment is of a size sufficient to process a sheet of film having up to a 71.12 centimeter length as measured in the direction of travel of the sheet. Also, for a drum width of 48.26 centimeters, the maximum width of a sheet of film 14 to be processed would be about 35.56 centimeters. Any size flexible sheet which is smaller than the stated maximum dimensions could be processed on the plate processor 10 of the first preferred embodiment.

A controller (not shown) is provided and is programmable by a control panel 50 (shown in Figure 2). When the machine is turned on, the preheating drum 18 is in the "start" position. In the "start" position, a trailing edge of the clamp 20 is in close proximity with the feed plate 70 shown in detail in Figure 4. A guide plate 84 is pivotally mounted above the feed surface 86. As the trailing edge of the flexible sheet of film 16 passes the leading edge 83 of guide plate 84, the guide plate pivots downwardly along pivotal axis 88 (into the paper) and engages a switch 90 generating a signal which is sent to and processed by the controller (not shown) to compute a "length" for the sheet of film. The controller uses this value at the end of the processing cycle to determine when to disengage the absorbent web 76 from the flexible sheet 16.

Clamp 20 holds the leading edge of the flexible sheet 16 onto an outer surface of the preheating drum 18 while the drum is rotating. A steady roller 92 is provided to hold the sheet 16 onto the drum surface 22 during rotation. The most preferred rotation speed is about 40.64 linear centimeters per minute at the drum surface 22. From the previous discussion, it would be possible to run the machine faster by increasing the operating temperature of the preheating drum 16. It would also be possible to operate the machine slower at a lower preheating temperature.

Steady roller 92 is positioned at approximately the uppermost location on the roller in the preferred embodiment to eliminate air between the film 16 and the outer surface 22 of the preheating drum 18 to apply a radial force to improve heat transfer to the roller 92. The roller 92 also holds the film 16 onto the drum 18 which extends slightly more than half way around the drum during processing.

Referring back to Figure 6, in order to raise the outer surface temperature of the flexible film 16 to a temperature which exceeds the melt temperature of the uncured portion of the radiation curable layer, a hot roller 78 is moved in the direction shown by arrow 94 until its outer surface contacts the leading edge 24 of the flexible sheet 16.

The hot roller 78 in the first preferred embodiment is driven by friction between its outer surface and the absorbent

web 76 contacting the roller 78. It is critical to the present invention that the linear speed of the hot roller 78, the web 76, and the film 16 be substantially the same to avoid any shear stress on the film. Such stress is known to cause uneven relief portion plate thickness, which is undesirable. The hot roller 78 rotates in a direction opposite the direction of rotation 72 of the preheating drum 18.

The web 76 originates from a supply roll 96 of absorbent material which in the preferred embodiment is mounted for rotation onto the stationary support frame 12. The web 76 of absorbent material passes over a first idler roller 98 which is positioned to deliver the web substantially horizontally to the hot roller 78. The absorbent material comes into face-to-face contact with the hot roller 78 which in the preferred embodiment is operated at a temperature of about 182°C (360 degrees Fahrenheit). Although the most preferred operating temperature of the heating roller is about 182°C (360 degrees Fahrenheit), it is known that the upper limit is determined in large part by the melting temperature of the web material 76 which in the preferred embodiment is 190°C (about 375 degrees Fahrenheit). Another temperature limitation is the melt temperature of the substrate. The substrate of the most preferred embodiment is a polyester film having a melt temperature of about 171°C (340 degrees Fahrenheit). Because the heat transfer is not at a steady state, hot roller 78 temperature of up to 190°C (375 degrees Fahrenheit) does not melt the substrate. The hot roller 78 temperature must also be low enough so that when the web 76 is not moving and the portions of the web contacting the hot roller 78 are at rest, the web 78 does not melt.

The controller (not shown), after measuring the length of the flexible sheet 16, and after receiving a signal from a cam operated microswitch 99 indicating that the leading edge 24 is at a point nearest the hot roller 78, actuates a pneumatic cylinder 100 which is fixedly mounted onto the stationary frame 12. The cylinder 100 extends, causing a movable frame 102 supporting the idler roller 98 and the hot roller 78 to move in a direction designated by arrow 94. In the preferred embodiment, tensioning springs 103 are provided between cylinder 100 and frame 102 to urge hot roller 78 against the film 16 at a selected pressure after the cylinder 100 has delivered the hot roller 78 to the "engaged" position.

Figure 8 is a schematic side elevational view of the device 10 with the hot roller 78 engaged. The nip 104, or distance between the hot roller 78 and the preheating drum 18 when the heating roller 78 is in the engaged position for this preferred embodiment is zero centimeters. It is desirable to set the distance such that a substantially uniform pressure of between 206.7 and 482.3 kPa (30 and 70 pounds per square inch), with a preferred pressure of about 310 kPa (45 psi) is applied to a surface of the flexible sheet of film 16 during processing.

Figure 8A shows a pressure limiting device 101 mounted onto a rotation shaft of the hot roller 78. The device 101 rides on an outer edge of drum 18 and limits the pressure exerted on the film 16.

Referring back to Figure 8, as the web 78 passes over the hot roller 78, its temperature is rapidly elevated to a temperature which must exceed the melt temperature of the polymer coating on the flexible sheet of film 16. The cylinder 100 in Figure 8 is in the extended position, with the heating roller 78 contacting the outer surface 22 of the preheating drum 18 and in intimate contact with both the web 76 and an outer surface of the flexible sheet 16. As the sheet 16 passes through the nip 104, a portion of the polymer coating liquifies and is absorbed into the web 76. According to the preferred embodiment, a single pass (one cycle) across hot roller 78 is insufficient to remove the full 0.381 millimeters of uncured material. For this reason, the controller (not shown) is programmed to allow the drum to rotate a total of three revolutions such that substantially all of the molten polymer can be absorbed onto the web 76.

Although the preferred embodiment requires three passes to remove all the molten polymer, it is to be understood that by selecting a different and more absorbent material with more favorable heat transfer characteristics, and by varying other parameters such as the thickness of the layer to be removed, it would be possible to achieve the desired absorption in fewer than three passes. Similarly, with other configurations, it would be necessary to pass the flexible sheet over the hot roller 78 more than three times.

After absorption, web 78 passes over a drive roller 106 which in the preferred embodiment is belt driven by a motor 108. In the preferred embodiment, motor 108 is a variable speed motor. The motor is of a size which will pull the web 76 through the device 10 at a linear speed which is synchronized with a linear speed of the outer surfaces of the preheating drum 18 and the hot roller 78.

The drive roller 106 in the first preferred embodiment has an abrasive outer surface. The roller 106 is preferably coated with an abrasive material such as sandpaper. The abrasive coating improves the frictional forces between the roller 106 and the web 76 and prevents slippage. The web 76 contacts at least one-third of the outer surface of the drive roller 106 in the preferred embodiment and loops over an idler roller 110 which aids in providing a substantially uniform tension to the web throughout the device 10. In addition to the idler roller 110, a brake 112 is provided which prevents the supply roll from unrolling too rapidly, for example, before the drive roller 106 pulls the web through.

A second idler roller 114 is optionally provided to further maintain tension on the web 76. After the web 76 exits from between rollers 110 and 114, the web 76 is directed through another pair of guide rollers 116 and 118 and is collected on a take-up roller 120.

Take-up roller 120 in the preferred embodiment is belt driven by a variable speed motor 122. This motor speed must be adjusted so as to not interfere with the selected web tension. If the motor interferes with web tension, a

flexographic plate formed in this manner could potentially have variable heights in the relief portions or might warp for example and be commercially unacceptable.

According to another preferred embodiment, a diameter sensor 124 is mounted onto the stationary frame 12 and measures the outer diameter of the absorbent material wound onto take-up roller 120. As the sensor 124 pivots, the output voltage from the sensor varies. In another preferred embodiment, a magnetic particle clutch (not shown) is mounted onto a rotating shaft supporting the take up roll 120, and the varying output voltage from sensor 124 varies the torque applied to the shaft to limit the rate of take-up. This clutch feature maintains substantially uniform tension on the portion of the web 76 near the take-up roll 120.

In another embodiment, the supply roll 96 is also equipped with a diameter sensor 126 which works in a substantially identical manner to sensor 124. The sensor 126 sends a signal to a magnetic particle brake (not shown) mounted onto a rotating shaft supporting the supply roll 96. The varying voltage varies the torque applied to the shaft supporting the supply roll 96, and maintains constant tension on the web 76. The magnetic particle brake is an example of an alternative device to replace the brake 112 to limit the unwinding of supply roll 96. The idler roller 110/drive roller 106 arrangement and magnetic particle brake delivers a web 76 having a uniform tension applied and that travels at a substantially constant rate of speed. In contrast, the brake 112 only roughly maintains tension in the web. The operation of brake 112 will be more completely described below.

In the most preferred embodiment, the guide roller 98, hot roller 78, drive roller 106, drive motor 108 and idler rollers 98 and 114 are all mounted onto a movable frame 102 actuated by a pneumatic cylinder 100.

The movable support structure 102 shown in Figures 8 and 9 is suspended from two spaced apart rods 128 and 130 which slide horizontally through a pair of support brackets 132 and 134 toward the preheating drum 18. Support brackets 132 and 134 in the preferred embodiment are secured to the stationary frame 12.

In operation, when the pneumatic cylinder 100 as shown in Figure 8 is actuated, the entire movable support structure 102 slides along spaced apart rods 128 and 130 until hot roller 78 contacts preheating drum 18. This position is referred to as the "running position".

The controller (not shown) in the preferred embodiment causes the assembly 102 to move into the running position as soon as a leading edge 24 (shown in Figure 6) of the flexible sheet 16 reaches the nip 104. The hot roller 78 raises the temperature of the web 76 in the preferred embodiment to about 360 degrees Fahrenheit. At this temperature, the uncured portions of the upper layer of the flexible film 16 in contact with the heated web liquify. Due to the heat transfer characteristics of the most preferred composite flexible film 16, it is necessary to separate the web 76 from the flexible sheet 16 immediately after absorption. This is accomplished by pulling web 76 away from the surface of the flexible film 16, in a direction of about 90 degrees from the direction of travel of the film 16, shown as angle 135. It is believed that pulling the absorbent material away at an angle of at least 45 degrees is necessary to release the formed plate before the liquified polymer cools and resolidifies. The preferred range of angles is between 75 and 105 degrees, and the most preferred angle is about 90 degrees. After the point of absorption at the nip 104, the flexible film 16 sags slightly and separates briefly from the preheating drum 18. By pulling the web 78 at an angle slightly below the horizontal, the flexible film 16 and web 76 rapidly separate. When the trailing edge of the flexible film 16 passes out of the nip 104, the controller (not shown) stops the drive motor 108, moves the hot roller 78 away from the drum 18 and rapidly advances the film 16 again so that the leading edge is returned to nip 104. This "rapid advance" feature causes the preheating drum 18 to rotate at 3 to 4 times the normal speed to save time, and improve machine capacity.

The brake 112 stops the travel of the web 76 while the preheating drum 18 is advancing to begin a new cycle. The brake 112 eliminates wasting unused web material 76. The device of the most preferred embodiment performs the absorption step three times on each sheet of flexible film 16.

At the conclusion of the third cycle, and as soon as a trailing edge of the flexible sheet 16 passes through the nip 104, the controller initiates a timing sequence utilizing the length measurement performed earlier to locate the trailing edge of the film 16. As soon as the film leaves the nip 104, the controller moves the hot roller 78 away from the film, and stops the drive motor 108. As the preheating drum 18 continues to rotate, cam operated microswitch 109 engages a cam on the drum 18 generating a signal received by the controller. The controller actuates a second pair of pneumatic cylinders 56 (shown in Figure 3) which releases a leading edge of the flexible sheet 16.

The leading edge of the formed flexographic plate is also assisted in being released from the drum by a stripper 136 which includes a pneumatic cylinder 138 pivotally mounted at one end to a lower surface of the feed tray 14. At the opposite end of the cylinder 138 is pivotally mounted a stripper blade 140 which in the preferred embodiment extends transversely across the width of drum 18. The most preferred stripper blade 140 has a plurality of fingers which extend to an outer surface of the drum 18 and mesh with the teeth 26 of clamp 20 (shown in Figure 2). The controller (not shown) at the conclusion of the third cycle, extends the stripper blade 140 until the blade contacts the outer surface of drum 18. A leading edge of a formed flexographic plate is gently lifted off the outer surface of drum 18, and the plate moves in the direction shown by arrow 142. In the most preferred embodiment, a conveyor 144 removes each formed flexographic plate from the device 10. Idler roller 168 which in the preferred embodiment is part of the conveyor 144 is positioned between the hot roller 78 and the stripper 136. This roller 168 drives the film 16 after the clamp 20 releases

the leading edge.

Referring back to Figure 9, a supply roll 96 of absorbent material 76 is mounted onto a shaft 146 equipped with tensioning means which in the preferred embodiment are brakes 148 and 150. Brakes 148 and 150 are formed from flexible straps, each strap fixedly mounted at a first end 152 (shown in Figure 8). The straps wrap around sheaves 154 and 156 which in the preferred embodiment have substantially smooth outer cylindrical surfaces. The sheaves 154 and 156 are fixedly mounted onto the supply roll shaft 146. The brakes 148, 150 according to the most preferred embodiment include flexible leather straps. The straps have first ends which are fixedly mounted 152 onto a stationary support 12 and have opposite ends equipped with tensioning springs 158 and 160 which are fixedly mounted onto the stationary frame 12.

In operation, brakes 148 and 150 provide tension on the web 76 as the web 76 is pulled through by the drive roller 106. The tension varies slightly as the diameter of supply roll 96 varies. In another preferred embodiment, a sensor 126 is provided for detecting the outside diameter of the supply roll 96. The sensor 126 is a potentiometer having a voltage which varies with pivotal position. The voltage output is sent to a magnetic particle brake (not shown) mounted onto shaft 146 which varies the torque output of the shaft 146. The magnetic particle brake and sensor 126 together maintain a substantially constant tension on the web 76.

Figure 10 is a side elevational view of the preheating drum 18 of a preferred embodiment of the present invention. A critical aspect of the present invention is to design the motion of the preheat roller 18 to achieve the smoothest possible rotation and to prevent backlash. A gear 162 is mounted onto a first end 164 of the preheating drum 18 and meshes with a pinion 163 at a point very near the outer surface 22 of the preheating drum 18. In the preferred embodiment, a brake consisting of an electrical circuit to reverse the direction of current supplied to the motor 73 is provided to stop the rotation of the preheating drum 18. This method of braking is commonly referred to as electro-dynamic braking. Referring to Figure 11, a central axis 166 of the pinion 163 shaft is closely spaced to the outer surface 22 of the preheating drum 18, such that the gear 162 and pinion 163 mesh at a point proximate the outer surface 22.

The idler roller 92 shown in Figure 10 in the preferred embodiment exerts minimal pressure, for example, only its own weight on the flexible sheet. Idler roller 92 forces entrained air out from beneath flexible film 16, and improves heat transfer from the drum 18 to the flexible film 16. An optional second idler roller 168 is spaced about 180 degrees from idler roller 92 and serves the purpose of driving the flexible film 16 after clamp 20 has released the leading edge. Idler roller 168 is also a part of a conveyor 144 (shown in Figure 8) for moving the formed plates from the device 10. In the preferred embodiment, roller 168 is spring loaded against drum 18.

Although the control scheme of the most preferred embodiment employs the use of cam operated switches and timers to control the device 10, Figure 10 shows an alternative device for controlling the operation of the present invention. In this embodiment, an encoder 170 is provided for generating a series of pulses to send to a number of counters. The counters are employed using known means to control the device 10.

Another aspect of the design of the preheating drum 18 of the preferred embodiment is illustrated in Figure 12. The preheating drum 18 is constructed to avoid stresses which could warp the surface of the drum and produce an unacceptable flexographic printing plate. The preheating drum 18 has a main wall portion 172. Mounted onto each end of the substantially cylindrical main wall portion 172 are hubs 174 and 176 which are held in place by four spaced apart tie-rods 178 extending through both hubs 174 and 176. Proximate the center of each tie-rod 178 is a tensioning spring 180 that has the function of holding the hubs 174 and 176 against the main wall portion 172 and at the same time allows the main wall portion 172 to freely expand in a direction substantially parallel to the axis of rotation.

The most preferred hub configuration is shown in Figure 13. Each hub 174, 176 is mounted onto a central stub shaft 182. In the preferred embodiment, one stub shaft 182 is hollow. The tie rods 178 are mounted onto arms 184, each being spaced apart by about 90 degrees. The design of the preheating drum 18 not only provides for expansion in the direction parallel to the axis of shaft 182 but it also allows for expansion in all directions.

The most preferred embodiment of the present invention is equipped with a heating blanket 21 (shown in Figure 4) mounted onto an inner surface of the main wall 172 of the preheating drum 18. The heating blanket 21 (shown in Figure 4) provides sufficient heat to provide an outer skin temperature of approximately 135°C (275 degrees Fahrenheit). One of the shafts 182 is hollow to provide an opening for the conductive wires of the heating blanket 21 to come into contact with a rotation contact pad (not shown).

Hubs 174 and 176 are also equipped with four slots 188 which in the preferred embodiment are spaced apart at approximately 90 degrees from each other for accepting keys (not shown) from the main wall section 172 of the drum 18. The slots 188 and keys (not shown) together assure that the main wall section 172 remains concentric with respect to the axis of rotation of the drum 18 and prevent relative rotational movement between the hubs 174 and 176 and the main wall portion 172.

Referring back to Figure 6, the outer surface of hot roller 78 is coated with a layer of elastomer coating 186. Although it is believed that a wide range of Shore A hardness units between about 30 and about 90 would be suitable to coat the hot roller 78, the most preferred rubber has a Shore A hardness of approximately 85 units. In the preferred embodiment, the rubber coating 186 is approximately 0.48 cm thick silicone rubber.

The heating roller 78 operates at a temperature of approximately 182°C (360 degrees Fahrenheit). Heat is provided to the heating roller 78 by a core heater available from Watlow Electric Company of St. Louis, Missouri. A cartridge heater having a 0.952 centimeter diameter, a 55.88 centimeter length and having 1450 watts power requiring a 220 volt supply would provide sufficient energy to maintain a skin temperature of approximately 360 degrees Fahrenheit. Although the heating roller of the preferred embodiment includes an electrical core heater, the present invention contemplates the use of steam, oil, hot air, and a variety of other heating sources to provide a skin temperature sufficient to melt a portion of the flexible film.

10 Claims

1. A device (10) for forming a flexographic printing plate (11) the plate being formed from a sheet of film having at least one layer (17) capable of being partially liquified, comprising:

heating means for applying heat to said sheet of film for an amount of time and at a temperature sufficient to cause a portion of said layer to liquify, the heating means comprising a hot roller (78) mounted for rotation into a first portion of a frame wherein the hot roller has an outer surface coated with an elastomer;
 first delivery means for supplying an absorbent material to a surface of said layer of said sheet of film;
 second delivery means for delivering the sheet of film to said heating means, wherein the second delivery means comprises a preheating drum (18) mounted for rotation in a second portion of the frame wherein at least one of the first and second frame portions are moveable relative to the other, wherein the preheating drum is formed from a substantially cylindrical wall portion (172), having a cavity defined by an inner surface of the cylindrical wall portion,
 a hub (174, 176) at each end, and means for attaching the hubs to the cylindrical wall portion to allow for thermal expansion,
 pressure means for causing a surface of said layer and the absorbent material to come into face to face contact between the preheating drum (18) and the hot roller (78) at a pressure sufficient for at least a portion of the liquified material to be absorbed by the absorbent material; and
 separation means for separating the film from the absorbent material.

2. The device of claim 1 wherein the second delivery means further comprises a gear (162) mounted onto an end of said drum (18), and a motor driven pinion (163) for engagement with said gear, wherein the gear (162) and pinion (163) mesh along a gear axis substantially parallel to an axis of rotation of the drum, and the gear axis is located substantially on an outer surface (22) of the drum.
3. The device of claim 1 wherein the heating means comprises a hot roller (78), wherein the hot roller has a central substantially cylindrical cavity, wherein a core heater is positioned in the cavity, and wherein the rate of rotation of the hot roller and operating temperature of the hot roller are selected to heat a continuous web of absorbent material contacting the hot roller (78) to a temperature sufficient to raise the temperature of the sheet of film above a melt temperature of said layer.
4. The device of claim 1 wherein the heating means comprises a heating blanket (21) mounted onto an inner surface of said preheating drum (18), wherein the heating blanket provides enough heat to raise a temperature of a flexible sheet to just below a melting temperature of said layer.
5. The device of claim 1 wherein the first delivery means comprises a drive roller (106) for delivering a continuous sheet of absorbent material to the heating means, the drive roller (106) being mounted for rotation into a support frame, wherein the drive roller comprises an abrasive substantially cylindrical outer surface.
6. The device of claim 1 wherein the first delivery means comprises a braking means (112), wherein the braking means comprises a tensioning means for limiting a rotation of a rotatable shaft (146) supporting a feed roll (96) of absorbent material to the heating means, wherein the tensioning means comprises a pair of spaced apart brakes (148, 150), each brake mounted onto said rotatable shaft, wherein each brake is formed from a spring biased flexible strap having a first end fixedly mounted (152) onto a support frame (12) and a second end connected to a spring (158, 160) the spring being fixedly mounted onto the support frame (12), the strap extending around a sheave (154, 156), the sheave being fixedly mounted onto a rotatable shaft (146) for supporting a supply roll of an absorbent web material, wherein the first delivery means comprise a rotating drive roller (106), wherein the tensioning means comprises at least one idler roller (110) in close contact with said drive roller, and wherein a web

passes between said drive roller and said idler roller.

7. The device of claim 1 wherein the preheating drum (18) is mounted for rotation in a stationary portion of a frame (12), wherein the heating means comprises a hot roller (78) mounted for rotation in a movable portion of said frame (102), wherein the movable portion of said frame (102) is moved to bring a surface of the hot roller into contact with a surface of the preheating drum (18), wherein the preheating drum (18) and hot roller (78) rotate in opposite directions, and move at substantially the same tangential speed, wherein a pressure limiting arm is mounted onto an axis of said hot roller (78) for engagement with a surface of the preheating drum (18) for limiting the pressure exerted on the flexible sheet, and wherein the separation means comprises at least one idler roller positioned to draw a web away from a surface of the flexible sheet of film after heating at an angle of at least about 45 degrees.
8. The device of claim 1 wherein the heating means comprises a heating blanket (21) mounted onto an inner surface of the preheating drum (18), and a hot roller (78), wherein the first delivery means further comprises a pneumatic means for moving a surface of the preheating drum proximate a surface of the hot roller, wherein the pneumatic means comprises a pneumatic cylinder (100), wherein the pressure means comprises spring means for maintaining pressure between the hot roller and preheating drum where the hot roller is mounted for rotation in a movable portion (102) of the frame, said movable portion (102) adapted to slide along a pair of bars (128, 130) attached to a stationary portion of said frame, wherein the pneumatic means comprises a pneumatic cylinder (100) attached at one end to a stationary portion of said frame, and attached to the movable portion of said frame at the opposite end.
9. The device of claim 1 wherein a clamping device (20) is mounted onto the preheating drum (18) and is positioned transversely on an outer surface (22), wherein the clamping device grips a leading edge (24) of the sheet of film (16), wherein the clamping device is elongated and comprises a plurality of teeth (26) which extends in a direction opposite the direction of travel of the sheet as the sheet contacts the drum, wherein each tooth has an edge on a lower surface facing an upper surface of the sheet of film for gripping the sheet when the clamping device is lowered onto an edge of the sheet, wherein the clamping device in the closed position is substantially flush mounted into an outer surface of said preheating drum (22), wherein the clamping device is spring (62) biased into a closed position, wherein the clamping device further comprises a rod (40) positioned transverse and substantially parallel to a central axis of the preheating roller, the bar being positioned between said axis and an inner surface of a wall of the preheating drum, and being fixedly attached to the elongated clamping device, further comprising actuation means (28), wherein the clamp is opened by the actuation means by applying pressure to the bar in a direction which is substantially radially outward, wherein the actuation means includes a pair of pneumatic cylinders (30), each cylinder applying a force to an end of the bar, wherein the bar includes a pair of cam followers (42) each having an outer surface for pressuring in a direction which is substantially radially outward from a rotational axis of said preheating drum, and wherein the separation means further comprises actuation means for opening the clamping means at a selected rotational position of the preheating drum so that a formed plate is released from the preheating drum.
10. The device of claim 1 wherein the preheating drum (18) is coated with an elastomer which is embedded with aluminum particles, wherein the elastomer used to cover the preheat drum has a hardness between 30 and 60 Shore A hardness units.
11. The device of claim 1 wherein the separation means comprises a stripper means (136) for releasing the heated sheet from the preheating drum (18), wherein the stripper means comprises an elongated stripper blade (140), wherein the stripper blade (140) is positioned transverse on a surface of the preheating drum (18), and is pivotally mounted to a first end of a pneumatic cylinder (138), the pneumatic cylinder being mounted at an opposite end to a support frame, wherein the transverse clamping device (20), is mounted onto an outer wall of the preheating drum, and wherein the scraper blade has a plurality of teeth portions which mesh with toothed portions (26) of the clamping device (20).
12. The device of claim 1 wherein the separation means comprises a conveyor (144) for removing a formed plate from the preheating roller, and for moving the formed plate to a selected location.
13. The device of claim 1 wherein the means for attaching the hubs (174, 176) comprises at least one key in the wall of the cylindrical wall portion (172), at least one key way (188) in the hub for accepting the key, and at least one tie rod (178) extending through the cavity defined by an inner surface of said cylindrical portion, the tie rod being segmented and connected to both hubs, and wherein the tie rod is formed of two substantially rod shaped portions,

the rod shaped portions being connected by a spring (180) to allow for thermal expansion.

14. The device of claim 1 wherein the separation means comprises a stripper blade (140), the first delivery means comprises a drive roller (106), and the heating means comprises a hot roller (78), and wherein the drive roller (106) and hot roller (78) are mounted onto a second frame (102) which moves relative to the first frame and further comprising:

control means for controlling the rotation of a drive roller (106) which moves a continuous web of absorbent material over the hot roller (78) for controlling the rotation of the preheating drum (18) for actuating a device for moving back and forth one of said frames, for opening a clamp (20) on the preheating drum, for controlling machine speed, for engaging the stripper blade (140), and for controlling hot roller (78) and preheating drum (18) temperatures according to a selected sequence.

Patentansprüche

1. Vorrichtung (10) zum Erzeugen einer flexographischen Druckplatte (11), welche Platte aus einem Blatt einer Folie erzeugt wird, die mindestens eine Schicht aufweist, die partiell verflüssigt werden kann, umfassend:

Mittel zum Erhitzen für das Aufbringen von Wärme auf das Blatt einer Folie für eine Zeitdauer und bei einer Temperatur, die ausreichend sind, um zu bewirken, daß ein Teil dieser Schicht verflüssigt wird, wobei das Mittel zum Erhitzen eine Heißtrommel (78) aufweist, die zur Rotation in einem ersten Abschnitt eines Rahmens befestigt ist und worin die Heißtrommel eine äußere Oberfläche aufweist, die mit einem Elastomer beschichtet ist;

erstes Fördermittel zum Zuführen eines absorbierenden Materials zu einer Oberfläche der Schicht dieses Folienblattes;

zweites Fördermittel für das Zustellen des Folienblattes zu dem Mittel zum Erhitzen, wobei das zweite Fördermittel eine Vorwärmtrommel (18) aufweist, die zur Rotation in einem zweiten Abschnitt des Rahmens befestigt ist und worin mindestens einer der ersten oder zweiten Rahmenabschnitte relativ zueinander beweglich sind, wobei die Vorwärmtrommel aus einem im wesentlichen zylindrischen Wandabschnitt (172) erzeugt wird und einen Hohlraum hat, der durch eine innere Oberfläche des zylindrischen Wandabschnittes begrenzt wird; eine Nabe (174, 176) an jedem Ende, sowie Mittel zum Anbringen der Naben an dem zylindrischen Wandabschnitt, um eine Wärmeausdehnung zuzulassen;

Mittel zum Druckerzeugen, um zu bewirken, daß eine Oberfläche dieser Schicht und das absorbierende Material einander zugewandt zwischen der Vorwärmtrommel (18) und der Heißtrommel (78) bei einem so ausreichenden Druck in Kontakt kommen, daß mindestens ein Teil des verflüssigten Materials von dem absorbierenden Material absorbiert wird; sowie

Mittel zum Trennen, um die Folie von dem absorbierenden Material zu trennen.

2. Vorrichtung nach Anspruch 1, bei welcher das zweite Fördermittel ferner ein Getrieberad (162) aufweist, das an einer Seite der Trommel (18) befestigt ist, sowie ein motorgetriebenes Zahnritzel (163) zum Eingriff mit dem Getrieberad, wobei das Getrieberad (162) und das Zahnritzel (163) entlang einer Radachse ineinandergreifen, die weitgehend parallel zu einer Rotationsachse ist, wobei die Radachse im wesentlichen auf einer äußeren Oberfläche der Trommel angeordnet ist.

3. Vorrichtung nach Anspruch 1, bei welcher das Mittel zum Erhitzen eine Heißtrommel (78) aufweist, wobei Heißtrommel einen zentralen, im wesentlichen zylindrischen Hohlraum hat, in welchem Hohlraum eine Kernheizung angeordnet ist und worin die Drehzahl der Heißtrommel und die Betriebstemperatur der Heißtrommel so ausgewählt werden, daß eine endlose Bahn des absorbierenden Materials, das die Heißtrommel (78) kontaktiert, auf eine Temperatur erhitzt wird, die ausreichend ist, um die Temperatur des Folienblattes oberhalb einer Schmelztemperatur der Schicht zu erhöhen.

4. Vorrichtung nach Anspruch 1, bei welcher das Mittel zum Erhitzen einen Heizmantel (21) aufweist, der auf einer Innenseite der Vorwärmtrommel (18) angebracht ist, wobei der Heizmantel ausreichend Wärme liefert, um eine Temperatur einer flexiblen Folie bis unmittelbar unterhalb einer Schmelztemperatur der Schicht zu erhöhen.

5. Vorrichtung nach Anspruch 1, bei welcher das erste Fördermittel eine Antriebsrolle (106) zum Zustellen eines endlosen flächigen absorbierenden Materials zu dem Mittel zum Erhitzen aufweist, wobei die Antriebsrolle (106) zur Rotation in einem Halterahmen eingebaut ist und wobei die Antriebsrolle eine abrasive, im wesentlichen zy-

lindrische äußere Oberfläche hat.

6. Vorrichtung nach Anspruch 1, bei welcher das erste Fördermittel ein Mittel zum Bremsen (112) aufweist, welches Mittel zum Bremsen eine Spannvorrichtung zum Begrenzen der Rotation einer rotationsfähigen Welle (146) aufweist, die eine Zuführrolle (96) von absorbierendem Material zum Mittel zum Erhitzen hält, wobei die Spannvorrichtung ein Paar beabstandeter Bremsen (148, 150) aufweist, die jede auf der rotationsfähigen Welle befestigt sind, wobei jede Bremse aus einem federbelasteten flexiblen Band mit einem ersten Ende erzeugt sind, das auf einem Halterahmen (12) fest angeordnet ist (152), sowie mit einem zweiten Ende, das mit einer Feder (158, 160) verbunden ist, wobei die Feder auf dem Halterahmen (12) fest aufgebaut ist und das Band um eine Rolle (154, 156) herumläuft, wobei die Rolle auf einer rotationsfähigen Welle (146) zum Halten einer Vorratsrolle für ein absorbierendes Bahnmaterial fest aufgebaut ist, wobei das erste Fördermittel eine rotierende Antriebsrolle (106) aufweist, wobei die Spannvorrichtung mindestens eine nichtangetriebene Rolle (110) im engen Kontakt mit der Antriebsrolle aufweist, und wobei eine Bahn zwischen der Antriebsrolle und der nichtangetriebenen Rolle hindurchläuft.
7. Vorrichtung nach Anspruch 1, bei welcher die Vorwärmtrommel (18) zur Rotation in einem stationären Teil eines Rahmens (12) eingebaut ist, wobei die Mittel zum Erhitzen eine Heißtrommel (78) aufweist, die zur Rotation in einem beweglichen Teil des Rahmens (102) befestigt ist, wobei der bewegliche Teil des Rahmens (102) so bewegt wird, daß eine Oberfläche der Heißtrommel in Kontakt mit der Vorwärmtrommel (18) gelangt, wobei die Vorwärmtrommel (18) und die Heißtrommel (78) zueinander entgegengesetzt rotieren und sich mit im wesentlichen gleicher Tangentialgeschwindigkeit bewegen, wobei der druckbegrenzende Hebel auf einer Achse der Heißtrommel (78) zum Eingriff mit einer Oberfläche der Vorwärmtrommel (18) befestigt ist, um den auf das flexible Folie ausgeübten Blatt zu begrenzen, und wobei das Mittel zum Trennen mindestens eine nichtangetriebene Rolle aufweist, die angeordnet ist, um eine Bahn von einer Oberfläche des flexiblen Folienblattes nach dem Erwärmen in einem Winkel von mindestens etwa 45 Grad abzuziehen.
8. Vorrichtung nach Anspruch 1, bei welcher das Mittel zum Erhitzen einen Heizmantel (21) aufweist, der auf einer inneren Oberfläche der Vorwärmtrommel (18) befestigt ist, und eine Heißtrommel (78), wobei das erste Fördermittel ferner ein pneumatisches Mittel aufweist, um eine Oberfläche der Vorwärmtrommel in die Nähe einer Oberfläche der Heißtrommel zu bewegen, wobei das pneumatische Mittel einen Pneumatikzylinder (100) aufweist, wobei das Mittel zum Druckerzeugen eine Federvorrichtung aufweist, um den Druck zwischen der Heißtrommel und der Vorwärmtrommel aufrechtzuerhalten, wobei die Heißtrommel zur Rotation in einem beweglichen Teil (102) des Rahmens befestigt ist, welches bewegliche Teil (102) so ausgelegt ist, daß es entlang eines an dem stationären Teil des Rahmens befestigten Stangenpaares (128, 130) verschieblich ist, wobei das pneumatische Mittel einen Pneumatikzylinder aufweist, der an dem einen Ende an einem stationären Teil des Rahmens befestigt ist und an dem gegenüberliegenden Ende an dem beweglichen Teil des Rahmens befestigt ist.
9. Vorrichtung nach Anspruch 1, bei welcher eine Spannvorrichtung (20) auf der Vorwärmtrommel (18) befestigt ist und quer auf einer äußeren Oberfläche (22) angeordnet ist, welche Spannvorrichtung eine Vorderkante (24) des Folienblattes (16) greift und welche Spannvorrichtung langgestreckt ist und eine Vielzahl von Zähnen (26) aufweist, die sich in einer zur Laufrichtung des Blattes entgegengesetzten Richtung ertrecken, wenn das Blatt mit der Trommel in Kontakt gelangt, wobei jeder Zahn eine Kante an einer unteren Oberfläche aufweist, die einer oberen Oberfläche des Folienblattes gegenübersteht, um das Blatt zu greifen, wenn die Spannvorrichtung auf eine Kante des Blattes abgesenkt wird, wobei die Spannvorrichtung in geschlossener Stellung im wesentlichen fluchtend in einer äußeren Oberfläche der Vorwärmtrommel (22) befestigt ist, wobei die Spannvorrichtung mit einer Feder (62) zu einer geschlossenen Stellung vorgespannt ist, wobei die Spannvorrichtung ferner eine quer angeordnete Stange (40) aufweist, die weitgehend parallel zur Mittenachse der Vorwärmtrommel ist, wobei die Stange zwischen der Achse und einer inneren Oberfläche einer Wandung der Vorwärmtrommel angeordnet ist und fest angebracht ist an der langgestreckten Spannvorrichtung, ferner umfassend Stellmittel (28), wobei die Spannvorrichtung durch das Stellmittel geöffnet wird, indem Druck auf die Stange in einer im wesentlichen radial nach außen orientierten Richtung gegeben wird, wobei das Stellmittel ein Paar Pneumatikzylinder (30) einschließt und jeder Zylinder eine Kraft auf ein Ende der Stange aufbringt, wobei die Stange ein Paar Nockenfolger (42) einschließt, die jeder eine äußere Oberfläche aufweisen, um in einer Richtung Druck zu erzeugen, die im wesentlichen von einer Rotationsachse der Vorwärmtrommel radial nach außen gerichtet ist und wobei das Mittel zum Trennen ferner Stellmittel zum Öffnen der Spannvorrichtung in einer ausgewählten Drehstellung der Vorwärmtrommel aufweist, so daß die erzeugte Platte aus der Vorwärmtrommel freigegeben wird.
10. Vorrichtung nach Anspruch 1, bei welcher die Vorwärmtrommel (18) mit einem Elastomer beschichtet ist, das mit

Aluminium-Partikeln eingebettet ist, wobei das zum Bedecken der Vorwärmtrommel verwendete Elastomer eine Härte zwischen 60 und 60 Shore A hat.

11. Vorrichtung nach Anspruch 1, bei welcher das Mittel zum Trennen einen Abstreifer (136) zum Ablösen des erhitzten Blattes von der Vorwärmtrommel (18) aufweist, wobei der Abstreifer ein längliches Abstreifermesser (140) aufweist, wobei das Abstreifermesser (140) quer auf einer Oberfläche der Vorwärmtrommel (18) angeordnet ist und gelenkig an einem ersten Ende eines Pneumatikzylinders (138) befestigt ist, wobei der Pneumatikzylinder an einem dem Halterahmen gegenüberliegenden Ende befestigt ist, wobei der Quer-Spannvorrichtung (20) auf einer äußeren Wandung der Vorwärmtrommel befestigt ist und wobei das Abstreifermesser eine Vielzahl von Zahnabschnitten aufweist, die mit den gezähnten Abschnitten (26) der Spannvorrichtung (20) ineinandergreifen.

12. Vorrichtung nach Anspruch 1, bei welcher das Mittel zum Trennen einen Förderer (144) aufweist, um eine erzeugte Platte von der Vorwärmtrommel zu entfernen und um die erzeugte Platte an einen ausgewählten Ort zu bringen.

13. Vorrichtung nach Anspruch 1, bei welcher das Mittel zum Anbringen der Naben (174, 176) mindestens einen Keil in der Wandung des zylindrischen Wandabschnittes (172) aufweist, mindestens eine Keilnut (188) in der Nabe zu Aufnehmen des Keils und mindestens eine Verbindungsstange (178), die sich durch den Hohlraum erstreckt, der durch eine innere Oberfläche des zylindrischen Abschnittes begrenzt wird, wobei die Verbindungsstange mit Segmenten versehen und mit beiden Naben verbunden ist und wobei die Verbindungsstange aus zwei im wesentlichen stabförmigen Abschnitten gebildet ist, welche stabförmigen Abschnitte über eine Feder (180) verbunden sind, um eine Wärmeausdehnung zuzulassen.

14. Vorrichtung nach Anspruch 1, bei welcher das Mittel zum Trennen ein Abstreifermesser (140) aufweist, das erste Fördermittel eine Antriebsrolle (106) aufweist und das Mittel zum Erhitzen eine Heißtrommel (78) aufweist und wobei die Antriebsrolle (106) und die Heißtrommel (78) auf einem zweiten Rahmen aufgebaut sind, der sich relativ zu dem ersten Rahmen bewegt und umfaßt:

Kontrollmittel, um in einer gewählten Folge die Rotation einer Antriebsrolle (106) zu kontrollieren, die ein endloses Band von absorbierendem Material über die Heißtrommel (78) bewegt; um die Rotation der Vorwärmtrommel (18) zu kontrollieren; um eine Vorrichtung zu betätigen, um einen der Rahmen zurück- und vorzubewegen; um eine Spannvorrichtung (20) auf der Vorwärmtrommel zu öffnen; um die Maschinengeschwindigkeit zu kontrollieren; um das Eingreifen des Abstreifermessers (140) zu kontrollieren; sowie um die Temperaturen von Heißtrommel (78) und Vorwärmtrommel (18) zu kontrollieren.

Revendications

1. Dispositif (10) de réalisation d'une plaque d'impression flexographique (11), la plaque étant formée d'une feuille de film comportant au moins une couche (17) pouvant être partiellement liquéfiée, comprenant :

des moyens de chauffage servant à appliquer de la chaleur à la feuille de film pendant une période de temps et à une température suffisantes pour faire se liquéfier une partie de la ladite couche, les moyens de chauffage comprenant un rouleau chauffant (78) monté rotatif dans une première partie d'un bâti, le rouleau chauffant présentant une surface extérieure revêtue d'un élastomère,

des premiers moyens d'acheminement servant à fournir une matière absorbante à une surface de la ladite couche de la feuille de film,

des seconds moyens d'acheminement servant à acheminer la feuille de film aux moyens de chauffage, les seconds moyens d'acheminement comprenant un tambour de préchauffage (18) monté rotatif dans une seconde partie du bâti, au moins l'une des première et seconde parties de bâti étant mobiles par rapport à l'autre, tandis que le tambour de préchauffage est constitué d'une partie de paroi (172) pratiquement cylindrique et présentant une cavité délimitée par une surface intérieure de la partie de paroi cylindrique,

un moyeu (174, 176) à chaque extrémité et des moyens servant à fixer les moyeux à la partie de paroi cylindrique de façon à permettre une dilatation thermique,

des moyens de pression servant à faire venir une surface de ladite couche et la matière absorbante en contact face à face, entre le tambour de préchauffage (18) et le rouleau chauffant (78) et à une pression suffisante pour qu'au moins une partie de la matière liquéfiée soit absorbée par la matière absorbante et des moyens de séparation servant à séparer le film de la matière absorbante.

2. Dispositif suivant la revendication 1, dans lequel les seconds moyens d'acheminement comprennent en outre une

roue dentée (162) montée sur une extrémité du tambour (18), et un pignon (163) entraîné par moteur, destiné à venir en prise avec la roue dentée, la roue dentée (162) et le pignon (163) engrènent le long d'un axe d'engrènement pratiquement parallèle à l'axe de rotation du tambour et l'axe d'engrènement est situé pratiquement sur la surface extérieure (22) du tambour.

3. Dispositif suivant la revendication 1, dans lequel les moyens de chauffage comprennent un rouleau chauffant (78), le rouleau chauffant présentant une cavité centrale pratiquement cylindrique, un élément de chauffage à noyau est disposé dans la cavité, et la vitesse de rotation du rouleau chauffant et la température de fonctionnement du rouleau chauffant sont choisies de façon à chauffer une nappe continue de matière absorbante, qui vient au contact du rouleau chauffant (78), à une température suffisante pour élever la température du de la feuille de film au-dessus de la température de fusion de ladite couche.
4. Dispositif suivant la revendication 1, dans lequel les moyens de chauffage comprennent un panneau chauffant (21) monté sur une surface intérieure du tambour de préchauffage (18), le panneau chauffant fournissant suffisamment une chaleur suffisante pour élever la température d'une feuille flexible jusqu'à une valeur située juste au-dessous de la température de fusion de ladite couche.
5. Dispositif suivant la revendication 1, dans lequel les premiers moyens d'acheminement comprennent un rouleau d'entraînement (106) servant à acheminer une feuille continue de matière absorbante aux moyens de chauffage, le rouleau d'entraînement (106) étant monté rotatif dans un bâti de support, et le rouleau d'entraînement comporte une surface extérieure pratiquement cylindrique abrasive.
6. Dispositif suivant la revendication 1, dans lequel les premiers moyens d'acheminement comprennent des moyens de freinage (112), les moyens de freinage comprennent des moyens de mise sous tension servant à limiter la rotation d'un arbre rotatif (146) portant un rouleau (96) d'alimentation des moyens de chauffage en matière absorbante, les moyens de mise sous tension comprennent deux freins espacés (148, 150), chaque frein monté sur l'arbre rotatif, chaque frein est formé d'une lame flexible à ressort dont une première extrémité (152) est montée à demeure sur un bâti de support (12) et la seconde extrémité est reliée à un ressort (158, 170), le ressort étant monté à demeure sur le bâti de support (12), la lame s'étendant autour d'une poulie (154, 156), la poulie étant montée à demeure sur l'arbre rotatif (146) servant à porter le rouleau d'alimentation un rouleau d'alimentation une matière en nappe absorbante, les premiers moyens d'acheminement comprennent un rouleau d'entraînement rotatif (106), les moyens de mise sous tension comprennent au moins un rouleau monté fou (110) en contact étroit avec le rouleau d'entraînement et une nappe passe entre le rouleau d'entraînement et le rouleau monté fou.
7. Dispositif suivant la revendication 1, dans lequel le tambour de préchauffage (18) est monté rotatif dans une partie fixée d'un bâti (12), les moyens de chauffage comprennent un rouleau chauffant (78) monté rotatif dans une partie mobile de bâti (102), la partie mobile de bâti (102) est déplacée de façon à amener la surface du rouleau chauffant en contact avec la surface du tambour de préchauffage (18), le tambour de préchauffage (18) et le rouleau chauffant (78) tournent dans des sens opposés et se déplacent pratiquement à la même vitesse tangentielle, un bras de limitation de pression est monté sur un axe du rouleau chauffant (78) pour venir en prise sur la surface du tambour de préchauffage (18) afin de limiter la pression exercée sur la feuille flexible et les moyens de séparation comprennent au moins un rouleau monté fou disposé de façon à tirer une nappe à l'écart de la surface de la feuille de film flexible, après chauffage, suivant un angle d'au moins environ 45 degrés.
8. Dispositif suivant la revendication 1, dans lequel les moyens de chauffage comprennent un panneau chauffant (21), monté sur une surface intérieure du tambour de préchauffage (18), et un rouleau chauffant (78), les premiers moyens d'acheminement comprennent en outre des moyens pneumatiques servant à amener la surface du tambour de préchauffage à proximité de la surface du rouleau chauffant, les moyens pneumatiques comprennent un vérin pneumatique (100), les moyens de pression comprennent des moyens formant ressort servant à maintenir une pression entre le rouleau chauffant et le tambour de préchauffage, le rouleau chauffant est monté rotatif dans une partie mobile (102) du bâti, la partie mobile (102) étant adaptée pour coulisser le long de deux barres (128, 130) fixées à une partie fixe du bâti, et les moyens pneumatiques comprennent un vérin pneumatique (100) fixé à une première extrémité à une partie fixe du bâti et fixé à la partie mobile du bâti à l'extrémité opposée.
9. Dispositif suivant la revendication 1, dans lequel un dispositif de serrage (20) est monté sur le tambour de préchauffage (18) et est disposé transversalement sur une surface extérieure (22), le dispositif de serrage serre un bord (24) de la feuille de film (16) qui est situé à l'avant dans le sens de déplacement, le dispositif de serrage a une forme allongée et comprend plusieurs dents (26) qui sont orientées dans un sens opposé au sens de dépla-

cement de la feuille lorsque la feuille est au contact du tambour, chaque dent présente une arête située sur une surface inférieure qui fait face à la surface supérieure de la feuille de film pour serrer la feuille lorsque le dispositif de serrage est abaissé sur un bord de la feuille, le dispositif de serrage est, dans la position fermée, monté pratiquement au niveau de la surface extérieure du tambour de préchauffage (22), le dispositif de serrage est sollicité par un ressort (62) dans une position fermée, le dispositif de serrage comprend en outre une barre (40) disposée transversalement et pratiquement parallèle à l'axe central du tambour de préchauffage, la barre étant disposée entre ledit axe et une surface intérieure d'une paroi du tambour de préchauffage et étant fixée à demeure au dispositif de serrage de forme allongée, comprenant en outre des moyens d'actionnement (28), le dispositif de serrage est ouvert par les moyens d'actionnement par application d'une pression à la barre dans un sens dirigé pratiquement radialement vers l'extérieur, les moyens d'actionnement comprennent deux vérins pneumatiques (30), chaque vérin appliquant une force à une extrémité de la barre, la barre comporte deux cames (42) présentant chacune une surface extérieure servant à appliquer une pression dans un sens dirigé pratiquement radialement vers l'extérieur à partir de l'axe de rotation du tambour de préchauffage et les moyens de séparation comprennent en outre des moyens d'actionnement servant à ouvrir les moyens de serrage pour une position angulaire déterminée du tambour de préchauffage de façon qu'une plaque formée soit libérée du tambour de préchauffage.

10. Dispositif suivant la revendication 1, dans lequel le tambour de préchauffage (18) est revêtu d'un élastomère dans lequel des particules d'aluminium sont enrobées, l'élastomère utilisé pour couvrir le tambour de préchauffage possède une dureté comprise entre 30 et 60 unités de dureté Shore A.


11. Dispositif suivant la revendication 1, dans lequel les moyens de séparation comprennent des moyens de décollement (136) servant à libérer la feuille chauffée du tambour de préchauffage (18), les moyens de décollement comprennent une lame de décollement (140) de forme allongée, la lame de décollement (140) est disposée transversalement sur la surface du tambour de préchauffage (18) et est montée pivotante à une première extrémité d'un vérin pneumatique (138), le vérin pneumatique étant monté à l'extrémité opposée sur un bâti de support, le dispositif de serrage transversal (20) est monté sur une paroi extérieure du tambour de préchauffage et la lame de décollement comporte de multiples parties formant dent qui s'intercalent avec des parties dentées (26) du dispositif de serrage (20).



12. Dispositif suivant la revendication 1, dans lequel les moyens de séparation comprennent un convoyeur (144) servant à retirer une plaque formée du tambour de préchauffage et à amener la plaque formée en un emplacement choisi.


13. Dispositif suivant la revendication 1, dans lequel les moyens servant à fixer les moyeux (174, 176) comprennent au moins une clavette disposée dans la paroi de la partie de paroi cylindrique (172), au moins une rainure de clavette (188) ménagée dans le moyeu pour recevoir la clavette et au moins un tirant (178) traversant la cavité délimitée par une surface intérieure de la partie cylindrique, le tirant étant segmenté et relié à l'un et l'autre moyeux, et le tirant est constitué de deux parties pratiquement en forme de tige, les parties en forme de tige étant reliées par un ressort (180) de manière à permettre une dilatation thermique.

14. Dispositif suivant la revendication 1, dans lequel les moyens de séparation comprennent une lame de décollement (140), les premiers moyens d'acheminement comprennent un rouleau d'entraînement (106), les moyens de chauffage comprennent un rouleau chauffant (78) et le rouleau d'entraînement (106) et le rouleau chauffant (78) sont montés sur un second bâti (102) qui se déplace par rapport au premier bâti, comprenant en outre :
des moyens de commande servant à commander la rotation du rouleau d'entraînement (106) qui déplace une nappe continue de matière absorbante sur le rouleau chauffant (78), à commander la rotation du tambour de préchauffage (18), à actionner un dispositif servant à déplacer dans un sens et dans l'autre l'un desdits bâtis, à ouvrir un dispositif de serrage (20) situé sur le tambour de préchauffage, à commander la vitesse de la machine, à mettre en prise la lame de décollement (140) et à commander les températures du rouleau chauffant (78) et du tambour de préchauffage (18) suivant une séquence choisie.

Fig. 1










Fig. 11







Fig. 5



HEAT UP CURVES
FOR POLYMER/FILM*Fig. 7A*HEAT UP CURVES
FOR POLYMER/FILM*Fig. 7B*



HEAT UP CURVES
FOR POLYMER/FILM*Fig. 7C*HEAT UP CURVES
FOR POLYMER/FILM*Fig. 7D*

Fig. 8





Fig. 8A







Fig. 9






Fig. 13

THIS PAGE LEFT BLANK